



Polymer Concrete Retarder

Data Sheet

Part # PCR-1

DESCRIPTION:

Polymer Concrete Retarder slows down the set time in polymer mixes. It can be easily added to Stamp-Top™, Spray-Top®, Resurfacer, Texture-Top™ and Trowel-Top™. It is recommended to add to polymer mixes when temperatures are above 70° F (21.1° C).

FEATURES & BENEFITS:

- Slows down drying time for concrete in high temperatures
- Allows the spreading and stamping crew more time to work the material
- Can keep Spray-Top mix fresh for 3 – 4 days, when covered with water and sealed with bucket lid

APPLICATION INSTRUCTIONS:

Once a surface has been patched, cleaned, dried and prepped for concrete begin mixing Concrete Solutions Stamp-Top. Using a drill mixer, mix 1 gallon (3.8 liters) of water, colorpaks (optional) and 4 - 6 oz (29.6 ml) of Concrete Polymer Retarder. At your own discretion, add more or less Concrete Polymer Retarder to adjust the drying time for your stamping conditions. Add in entire Stamp-Top bag mix and mix for 3 – 5 minutes. The Stamp-Top mix consistency will vary depending on ambient temperatures and humidity. If needed, add up to 1 quart (1.1 liters) of additional water per bag mix.

HOW SUPPLIED:

Polymer Concrete Retarder is available in 1 gallon container.

SAFETY PRECAUTIONS:

Health Considerations: Consult the Rhino Linings® Safety Data Sheets (SDS)

Chemical systems require the use of proper safety equipment and procedures. Please follow the Rhino Linings® product SDS and Safety Manual for detailed information and handling guidelines.

For Your Protection: The information and recommendations in this publication are, to the best of our knowledge, reliable. Suggestions made concerning the products and their uses, applications, storage and handling are only the opinion of Rhino Linings Corporation. Users should conduct their own tests to determine the suitability of these products for their own particular purposes and of the storage and handling methods herein suggested. The toxicity and risk characteristics of products made by Rhino Linings Corporation will necessarily differ from the toxicity and risk characteristics developed when such products are used with other materials during a manufacturing process. The resulting risk characteristics should be determined and made known to ultimate end-users and processors.

Because of numerous factors affecting results, **Rhino Linings Corporation makes no warranty of any kind, express or implied**, other than that the material conforms to its applicable current Standard Specifications. Rhino Linings Corporation hereby disclaims any and all other warranties, including but not limited to those of merchantability or fitness for a particular purpose. No statements made herein may be construed as a representation or warranty. The liability of Rhino Linings Corporation for any claims arising from or sounding in breach of warranty, negligence, strict liability, or otherwise shall be limited to the purchase price of the material.

©2016 Rhino Linings Corporation. All rights reserved.

Rhino Linings Corporation

9747 Businesspark Avenue, San Diego, CA 92131
858-450-0441 • Fax 858-450-6881
1-800-422-2603
www.rhinolinings.com

Concrete Solutions by Rhino Linings

7455 Carroll Road, San Diego, CA 92121
1-800-232-8311 • Fax 858-566-4346
www.concretesolutions.com