



Stamped Concrete Sealer Data Sheet

Part # SCS, SCS-VOC

DESCRIPTION: Concrete Solutions® Stamped Concrete Sealer is a single component, clear acrylic formulation developed to provide a hard, glossy, protective film to beautify and protect regular concrete, stamped concrete, exposed aggregate and other masonry surfaces. It is easy to apply, fast drying, ultraviolet stable, non-yellowing under extreme exposure and provides a tough, durable, ultra clear finish with excellent abrasion, chemical and stain resistance. It is available in two versions, regular and VOC compliant for areas with strict VOC laws such as in Arizona and California.

TYPICAL USES: Stamped Concrete Sealer is used indoors and outdoors on driveways, patios, pool decks, sidewalks and interior floors where a long lasting, tough, stain resistant finish is desired. Stamp Concrete Sealer is the most commonly used sealer over the Concrete Solutions 1/4" Stamping System and can also be used to seal and protect exposed aggregate surfaces to provide a wet-look appearance. It is sometimes mixed with Antique Powders to add color or antiquing to stamping applications.

FEATURES & BENEFITS:

- Non-yellowing protective sealer
- Easy to apply

CHEMICAL PROPERTIES:

	Result
Solids by Weight	28%
Volatile Organic Compounds	580 g/l : 400 g/l (VOC version)
Recoat	30 – 60 min
Dry to Touch at 70°F	30 – 60 min
Walk on Time (light foot traffic)	4 – 6 hrs
Coverage Rate per Gallon	200 – 300 sqft
Recommended Application Temperature	≥50°F (≥10°C)
Color	clear

TYPICAL PHYSICAL PROPERTIES:

	Result
Adhesion to concrete	concrete fails before sealer
Tukon Hardness	16

MOISTURE VAPOR TESTING: All concrete floors not poured over a proper moisture barrier, are subject to possible moisture vapor transmission or hydrostatic pressure problems which can cause a coating system to blister or fail. Before applying a coating system over a concrete floor which is on-grade or below grade, the customer should be informed of this potential problem and given the option to have a qualified moisture testing company perform calcium chloride test to give the proper recommendations.

SURFACE PREPARATION: The surface must be clean and sound, free from oil, dirt, waxes and any other contaminants that may interfere with bonding. The most common method is: scrubbing with detergent, acid washing, neutralizing and pressure washing. Existing coating materials should be removed, or if in good condition sanded with a floor polisher machine with a sandpaper attachment and 80 grit sandpaper to lightly scratch and dull the surface. Note: Going over existing coatings is up to the discretion of the applicator. It is not recommended to apply it over concrete with curing or sealing membranes. (See Concrete Solutions Training Manual for more detailed information.)

APPLICATION INSTRUCTIONS: For most applications, it is best to apply a first coat thinned 1 to1 with acetone (where local laws permit) then a second coat straight or thinned up to 25%. For extra gloss, a third coat can be applied if desired. Where less gloss is desired, apply 1 – 2 coats thinned 1 to 1. Apply in thin, even coats by using a pump-up sprayer followed by back rolling or a HVLP or airless sprayer at low pressure for the best results. If using a pump-up type sprayer, it will need to be chemical resistant against solvents such as acetone (available from Rhino Linings Corporation or many Concrete Solutions distributors) and be capable of spraying a fine, even spray with out leaving drips or puddled areas. Avoid using in direct sunlight or during the hottest part of the day. After the first coat dries for 30 minutes to 1 hour, a second coat can be applied. For more information on 1/4" Stamping application including antiquing see Concrete Solutions Training Manual.

MAINTENANCE: Stamped Concrete Sealer can be cleaned with a light detergent and water. For interior floors, the sealer can be protected and maintained using a floor finish. For exterior applications, Stamp Concrete Sealer

CONCRETE SOLUTIONS® STAMPED CONCRETE SEALER *(continued)*:

should be re-applied every 18 – 24 months to maintain the finish. To reseal, clean the surface with a floor scrubber and detergent and pressure wash to rinse. Let the surface dry completely, then apply one coat of Stamp Concrete Sealer diluted 10 – 25% with acetone.

NOT RECOMMENDED FOR: Do not use on exterior flagstone, sandstone or slate. It is not recommended to apply it over concrete with curing or sealing membranes.

SUBSTRATES: Poured concrete, stamped concrete, exposed aggregate and other masonry surfaces

HOW SUPPLIED: Stamped Concrete Sealer is packaged in one gallon and five gallon pails.

SLIP/FALL PRECAUTIONS: Stamped Concrete Sealer can become slippery when wet especially on smooth surfaces. It is up to the end user's responsibility to determine the suitability of the Stamped Concrete Sealer for their particular application. Slip resistant granules such as glass beads or #80 – 100 white aluminum oxide granules can be incorporated into the wet Stamped Concrete Sealer to provide whatever degree of slip resistance is necessary. Concrete Solutions or its sales people will not be responsible for injury incurred in a slip/fall accident.

WARNING: Stamped Concrete Sealer is combustible and should be kept away from open flames. Turn out all pilot lights. Wear the proper breathing mask in areas with poor ventilation. Read Safety Data Sheet before using. For professional use only!

SAFETY PRECAUTIONS: Health Considerations: Consult the Rhino Linings® Safety Data Sheets (SDS)

Chemical systems require the use of proper safety equipment and procedures. Please follow the Rhino Linings® product SDS and Safety Manual for detailed information and handling guidelines.

For Your Protection: The information and recommendations in this publication are, to the best of our knowledge, reliable. Suggestions made concerning the products and their uses, applications, storage and handling are only the opinion of Rhino Linings Corporation. Users should conduct their own tests to determine the suitability of these products for their own particular purposes and of the storage and handling methods herein suggested. The toxicity and risk characteristics of products made by Rhino Linings Corporation will necessarily differ from the toxicity and risk characteristics developed when such products are used with other materials during a manufacturing process. The resulting risk characteristics should be determined and made known to ultimate end-users and processors.

Because of numerous factors affecting results, **Rhino Linings Corporation makes no warranty of any kind, express or implied**, other than that the material conforms to its applicable current Standard Specifications. Rhino Linings Corporation hereby disclaims any and all other warranties, including but not limited to those of merchantability or fitness for a particular purpose. No statements made herein may be construed as a representation or warranty. The liability of Rhino Linings Corporation for any claims arising from or sounding in breach of warranty, negligence, strict liability, or otherwise shall be limited to the purchase price of the material.

©2014 Rhino Linings Corporation. All rights reserved.



Rhino Linings Corporation

9747 Businesspark Avenue, San Diego, CA 92131
858-450-0441 • Fax 858-450-6881
1-800-422-2603
www.rhino linings.com

Concrete Solutions by Rhino Linings

7455 Carroll Road, San Diego, CA 92121
1-800-232-8311 • Fax 858-566-4346
www.concretesolutions.com