

BioSeal™ 10.0 Black – Part # BSL100-B SET

DESCRIPTION: BioSeal™ 10.0 is a water-blown, closed cell, spray polyurethane foam sealants. BioSeal 10.0 has a nominal density of 10.0 pounds per cubic foot. It is ideal for use in agricultural and industrial applications. When installed by an approved contractor, BioSeal expands to fill voids, crevices, and cavities, thereby reducing air and moisture flow. This high density polyurethane foam resists the harsh environments typically seen in industrial/agricultural applications. Available in white and black.

TYPICAL USES:

- Sealants for use in agricultural or industrial buildings
- Exterior and below-grade applications
- Tanks/silos
- Industrial duct work
- Soil stabilization

FEATURES & BENEFITS:

- Low VOC
- Adheres to and seals practically any sound surface
- Immediate bond
- Acts as a vapor retarder and air barrier
- Reduces condensation potential

CHEMICAL PROPERTIES:	Standard Test	Isocyanate (A)	Resin (B)
Specific Gravity (grams/cc)	ASTM D-792	1.2	1.18
Viscosity, CPS at 77°F (25°C)		200	1000 – 1400
Solids by Volume/Weight		100%	100%
Volatile Organic Compounds		0 g/l	0 g/l
Mix Ratio, Parts per Volume		1	1
Gel Time, Seconds at 77°F (25°C)		4 – 7	
Tack-free, Seconds		8 – 12	
Shelf Life - Unopened Containers		12 months	6 months
Base Color		brown	amber

TYPICAL PHYSICAL PROPERTIES:	Test	Result
Density, core (pcf)	ASTM D-1622	10.0 ± 0.2
Tensile Strength (psi)	ASTM D-1623	60 – 70
Compressive Strength (psi)	ASTM D-1621	140 – 180
Closed-Cell Content (%)	ASTM D-2856	>90%
Water Vapor Permeability* (perm)	1.5" (38 mm) ASTM E-96	<1 perm per inch
Air Permeability** (L/s/m² @ 75 Pa)	ASTM E-283	.003
Dimensional Stability (%) at 158 ± 4° F (70 ± 2° C) Ambient Humidity at 73 ± 4° F (23 ± 2° C) 50% Relative Humidity	ASTM D-2126	<12% change
Surface Burning Characteristics 2" Sample (102 mm)		
Fire Rating	ASTM E-84	non-rated
Flame Spread Index	ASTM E-84	non-rated
Smoke Development Index	ASTM E-84	non-rated

PROCESS TEMPERATURE AND ENVIRONMENT CONDITIONS: The system settings required to achieve quality spray sealant application will vary depending on environmental and substrate conditions. The following recommended parameters will help ensure optimum sealant quality.

Iso (A) & Resin (B) Components	Hose	Static Pressure
120 – 140° F (49 – 60° C)	120 – 140° F (49 – 60° C)	1000 – 1400 psi (82.7 to 110 bar)

Substrate Surface	Substrate Moisture	Maximum Service Temperature
50 – 120° F (10 – 49° C)	Substrate must be dry, < 12% WMC	< 180° F (< 82.2° C)

PREPARATION: While prepping equipment, heating drums and re-circulating for spray foam application, agitate the 'B' component mildly using a pneumatic or equivalent performing mixer. Mild agitation may be necessary, not to exceed 4 hours per day.

Depth per pass of BioSeal 10.0 should be between ½" (12.7 mm) and ¾" (19 mm).

Thin passes (¼" (6.35 mm) or less) should be avoided and may result in reduced yield. Allow a 4 to 6 second time interval between passes to allow foam to cure and reduce the likelihood of blowing the reacting material away from the substrate. *It is important that applicators review and understand the training manual prior to use or application of BioSeal.*

APPLICATION INSTRUCTIONS: BioSeal must be installed by approved contractors who have successfully completed an approved training program or Rhino Linings approved field certification program which covers proper application techniques, environmental health and safety.

Enovate® 245fa blown foams followed by BioSeal water blown foam: When using BioSeal after an Enovate 245fa blown spray polyurethane foam it is necessary to flush the B-side lines with a non-water based solvent in order to achieve maximum foam quality and yield.

Water blown foams followed by BioSeal: Flushing the system with solvent may not be necessary when switching from one water blown foam system to the next, but it is imperative that any remaining product from the previous application is completely removed or flushed from applicator guns, B-side lines and pumping system by a through-put of BioSeal product until test sprays indicate that no mixed foam is present in the system.

When flushing or purging lines, never spray polyurethane foam into large, thick piles as the heat generated during the curing process can cause spontaneous combustion. Before adding additional foam, ensure that the core temperature is less than 150° F (66° C).

NOT RECOMMENDED FOR: This product is not intended for use in residential or commercial structures.

SUBSTRATES: Bonds to virtually all clean and dry substrate of any dimension

HOW SUPPLIED: Net weight per set is 960 pounds (435 kg). A set of BioSeal consists of one (1) 55 gallon (208 L) drum of 'A' component and one (1) 55 gallon (208 L) drum of 'B' component.

STORAGE: BioSeal should be stored between 60 – 90° F (15.6 – 32.2° C) out of direct sunlight. Conditioned trailers or storage areas may be necessary.

SAFETY PRECAUTIONS: Health Considerations: Consult the Rhino Linings® Safety Data Sheets (SDS)

Chemical systems require the use of proper safety equipment and procedures. Please follow the Rhino Linings® product SDS and Safety Manual for detailed information and handling guidelines.

For Your Protection: The information and recommendations in this publication are, to the best of our knowledge, reliable. Suggestions made concerning the products and their uses, applications, storage and handling are only the opinion of Rhino Linings Corporation. Users should conduct their own tests to determine the suitability of these products for their own particular purposes and of the storage and handling methods herein suggested. The toxicity and risk characteristics of products made by Rhino Linings Corporation will necessarily differ from the toxicity and risk characteristics developed when such products are used with other materials during a manufacturing process. The resulting risk characteristics should be determined and made known to ultimate end-users and processors.

Because of numerous factors affecting results, **Rhino Linings Corporation makes no warranty of any kind, express or implied**, other than that the material conforms to its applicable current Standard Specifications. Rhino Linings Corporation hereby disclaims any and all other warranties, including but not limited to those of merchantability or fitness for a particular purpose. No statements made herein may be construed as a representation or warranty. The liability of Rhino Linings Corporation for any claims arising from or sounding in breach of warranty, negligence, strict liability, or otherwise shall be limited to the purchase price of the material.

* ASHRAE defines a Class III vapor retarder as a material having between 1 and 10 perms.

** The International Residential Code defines air impermeable as having less than 0.02 L/m-s at 75 Pa.

©2015 Rhino Linings Corporation. All rights reserved.