

# RhinoArmor™ PPFR 1150 Data Sheet

Part A – RhinoArmor™ PPFR 1150 Iso – Part # 60042-1 Part B – RhinoArmor™ PPFR 1150 Resin – Part # 60044-1

**DESCRIPTION:** RhinoArmor PPFR 1150 is a two component, flame retardant, elastomeric 100% polyurea system. Its flame retardence makes it an ideal coating for numerous applications that require a flammability rating. Because of the large number of flammability ratings and the large array of surfaces that can be coated, it is highly recommended that testing, certification and approval be considered prior to any application of this coating. Note: Ultimate flame retardence is dependent upon coated substrate, thickness and density.

### **TYPICAL USES:**

- Excellent fire retardant protective lining for abrasion, impact and corrosion resistance
- Spray-on application creates a monolithic, seamless lining which conforms to any shape and size.
- Tough, durable lining for military applications such as:
  - Tactical vehicles and equipment requiring abrasion, corrosion and impact protection
  - Foot traffic areas requiring non-slip surfaces
- Excellent blast mitigation properties for military barracks, vehicles, temporary structures and buildings.
  - High tensile and elongation properties contain and reduce shrapnel in vehicles and buildings
- · Can withstand tracked vehicle traffic and heavy loads with proper thickness build
- Reduces noise from vibration and impact
- Spray-on application creates a monolithic, seamless lining which conforms to any shape and size
- Can withstand vehicle forklift traffic and heavy loads with proper thickness build

## **FEATURES & BENEFITS:**

- Can be applied in 100% humidity and in cold temperatures as low as -32°F (-36°C)
- Maximum thickness unlimited
- Excellent abrasion resistance
- Excellent impact resistance
- Excellent chemical resistance

- Excellent fire resistance
- Excellent weather resistance
- Excellent corrosion resistance
- · High tensile strength, elongation and tear strength
- Provides vibration and acoustic dampening

IEMICAL PROPERTIES:	Standard Test	Isocyanate (A)	Resin (B)
Specific Gravity (grams/cc)	ASTM D-792	1.18 – 1.2	0.9 – 1.02
Viscosity, CPS at 77°F (25°C)		400	650
Solids by Volume/Weight		100%	100%
Volatile Organic Compounds, cal	culated	0 lbs/gal	0 lbs/gal
Mix Ratio, Parts per volume		1	1
Mix Ratio, parts per weight		109	100
Gel Time, seconds at 77°F (25°C		7 – 10	
Tack-free, seconds		10 – 12	
Theoretical Coverage (dft)		1600 sqft/gal at 1 mil	thick
Base Color		amber	straw opaque
Shelf Life - Unopened Containers	S	12 months	12 months
Shelf Life - Unopened Containers  PICAL PHYSICAL PROPERTI		12 months  Test	12 months  Result
·			
PICAL PHYSICAL PROPERTI		Test	Result
PICAL PHYSICAL PROPERTI Hardness (Shore D)		Test ASTM D-2240	Result 50±5
PICAL PHYSICAL PROPERTI Hardness (Shore D) Tensile Strength (psi)*		Test ASTM D-2240 ASTM D-412	Result 50±5 2200
PICAL PHYSICAL PROPERTI Hardness (Shore D) Tensile Strength (psi)* Tear Resistance (pli)** Die C		Test ASTM D-2240 ASTM D-412 ASTM D-624	Result 50±5 2200 600
PICAL PHYSICAL PROPERTION Hardness (Shore D) Tensile Strength (psi)* Tear Resistance (pli)** Die C Elongation (%)*		Test  ASTM D-2240  ASTM D-412  ASTM D-624  ASTM D-412	Result 50±5 2200 600 200
PICAL PHYSICAL PROPERTION Hardness (Shore D) Tensile Strength (psi)* Tear Resistance (pli)** Die C Elongation (%)*		Test  ASTM D-2240  ASTM D-412  ASTM D-624  ASTM D-412  FMV-302	Result 50±5 2200 600 200 Pass
PICAL PHYSICAL PROPERTION Hardness (Shore D) Tensile Strength (psi)* Tear Resistance (pli)** Die C Elongation (%)*		Test  ASTM D-2240  ASTM D-412  ASTM D-624  ASTM D-412  FMV-302  Cal 117	Result  50±5 2200 600 200 Pass Pass (Uncertified)

#### RHINOARMOR™ PPFR 1150

TYPICAL PHYSICAL PROPERTIES (continued):	Test	Result	
Dielectric Constant (MHz)	ASTM I	D-150 5.4	
Dissipation Factor (MHz)	ASTM I	D-150 0.058	
Cathodic Disbonding	ASTM (	G-8 Pass	

<sup>\*</sup>Properties were checked of RhinoArmor PPFR polyurea lining, 1/8" (125 mils), (3.18 mm) thick stock.

#### PROCESSING CHARACTERISTICS:

Equipment Used	Spray Pressure	Process Pressure	Spray Gun	Mix Module
Graco EXP-2	2000 psi	2300 – 3500 psi	Fusion - Air Purge or Mechanical Purge	AR2929 or greater

#### **Process Temperatures**

Component Temperature (A&B)	Hoses - High Pressure	Substrate Surface
150°F (66°C)	150°F (66°C)	60° – 110°F (15° – 43°C)

#### DRY FILM THICKNESS RANGE:

Varies based on application, typically used at a minimum of 1/16" (62.5 mils; 1.5 mm) up to unlimited thickness)

# **CHEMICAL RESISTANCE:**

(Guidelines only: Fume, splash, spillage as noted. Individual testing required for immersion).

Properties were check from RhinoArmor PPFR lining, 1/8" (125 mils), (3.18mm) thick stock.

SUBSTRATES: Metals, wood, concrete, fiberglass, geotextiles and most plastics

**COLOR OPTIONS:** Standard colors - black. Custom colors are available by special order.

**HOW SUPPLIED:** Net weight per set is 910 pounds (412.8 kg). A set of RhinoArmor PPFR 1150 consists of one (1) 55 gallon (208 L) drum of 'A' component and one (1) 55 gallon (208 L) drum of 'B' component.

# SAFETY PRECAUTIONS: Health Considerations: Consult the Rhino Linings® Safety Data Sheets (SDS)

This chemical system requires the use of proper safety equipment and procedures. Please follow the Rhino Linings® product SDS and Safety Manual for detailed information and handling guidelines.

For Your Protection: The information and recommendations in this publication are, to the best of our knowledge, reliable. Suggestions made concerning the products and their uses, applications, storage and handling are only the opinion of Rhino Linings Corporation. Users should conduct their own tests to determine the suitability of these products for their own particular purposes and of the storage and handling methods herein suggested. The toxicity and risk characteristics of products made by Rhino Linings Corporation will necessarily differ from the toxicity and risk characteristics developed when such products are used with other materials during a manufacturing process. The resulting risk characteristics should be determined and made known to ultimate end-users and processors.

Because of numerous factors affecting results, **Rhino Linings Corporation makes no warranty of any kind, express or implied,** other than that the material conforms to its applicable current Standard Specifications. Rhino Linings Corporation hereby disclaims any and all other warranties, including but not limited to those of merchantability or fitness for a particular purpose. No statements made herein may be construed as a representation or warranty. The liability of Rhino Linings Corporation for any claims arising from or sounding in breach of warranty, negligence, strict liability, or otherwise shall be limited to the purchase price of the material.

©2016 Rhino Linings Corporation. All rights reserved.

